



Aitken Freeman Pty Ltd
Factory 7, 7-9 Brough St, Springvale Vic 3171
PO Box 548, Noble Park Vic 3174
Ph: 03 9701 3955 Fax: 03 9701 3956
Web: www.aitkenfreeman.com
email: sales@aitkenfreeman.com

Resigrout S

High strength epoxy grout

INTRODUCTION

Resigrout S is a high strength epoxy grout, based on specially selected epoxy resins, hardeners and aggregates. Resigrout S is ideal for installation of equipment, chemical anchoring and general grouting.

BENEFITS

- High strength
- Excellent adhesion
- Cures under damp conditions
- Ease of application
- Economical cost of material
- Prepackaged for onsite blending

PREPARATION

The areas to be filled with Resigrout S must be free of oil, grease or other contaminants which may affect adhesion of the product. Loose concrete or other material should be removed from the surface prior to the application of the Resigrout S.

MIXING

Resigrout S is a 2 part epoxy system, the Hardener component should be added to the Base and mixed using an electric drill and a suitable mixing paddle. Mix thoroughly for 3 – 5 minutes to ensure uniformity of consistency and colour. Only mix as many kits as can be applied within the pot life of the product.

APPLICATION

Resigrout S can be installed by pouring the mixed material from the original Base container. Ensure all voids are completely filled and trowel off to required standard. Use all mixed product within the pot life. Do not attempt to rework or retemper cured product.

CURING

Resigrout S will dry to a tack free finish within 24 hours. Full cure is reached after 7 days.

CLEAN UP

All equipment should be cleaned immediately after use using Resiloc Thinners. Cured material can only be removed with difficulty.

TYPICAL PROPERTIES

Compressive strength	85 Mpa
Tensile Strength	25 Mpa
Flexural Strength	32MPa
Pot Life @ 20°C	45 minutes
Full Cure	7 days

SUPPLY

Resigrout S is available in either 3 litre or 15 litre kits. Resigrout S should be stored in a cool, dry place in original unopened containers. Shelf life under these conditions is 12 months.

PRECAUTIONS

Resigrout S is designed for use in ambient temperatures between 10° - 35° C and all properties listed above assume a temperature of 20°C. Where conditions outside this range are encountered, please consult our technical staff prior to application.

Always read the product data sheet, MSDS and product label prior to use of this material.

ALLIED PRODUCT RANGE

Aitken Freeman Pty Ltd is an Australian company which manufactures and distributes a broad range of construction products including grouts and anchoring systems, surface coatings, concrete admixtures, adhesives and sealants, floor levelling, and concrete repair products. Call our office for more information.

Refer to Material Safety Data Sheet for precautions and personal protection prior to use of this product

Disclaimer: Any advice, recommendation, information, assistance or service provided by Aitken Freeman Pty Ltd in relation to goods manufactured or supplied by them or their use and application is in good faith and is believed by Aitken Freeman Pty Ltd to be appropriate and reliable. However, any advice, recommendation, information, assistance or service provided by Aitken Freeman Pty Ltd is provided without liability.