


# Resigrout L



## High strength fluid Epoxy Grout

### USES

Resigrout L is a high strength, fluid epoxy grout based on specially selected epoxy resins and hardeners. Resigrout L is ideal for chemical anchoring, underpinning base plates, crane rails and other equipment subject to dynamic loads.

### BENEFITS

- Excellent adhesion
- High strength
- Moisture tolerant - cures under damp conditions
- Ease of application and convenient mix ratio
- Economical cost of material

### TECHNICAL SUPPORT

Aitken Freeman offers a comprehensive range of high quality, high performance construction products. In addition, Aitken Freeman offers technical support to users and specifiers, and can arrange on-site visits to end users and contractors.

### PREPARATION

All cracks and holes to be grouted with Resigrout L should be clean and sound. Holes should be blown out with oil free compressed air to remove water or dust from the drilling of the hole. All contacted surfaces should be clean and free of oil, grease or other contaminants which could inhibit bond. Loose or damaged concrete should be repaired prior to application of Resigrout L or filled as part of the repair. Repairs can also be made with Resiloc PM, a non-slump epoxy patching mortar. Seal edges using Silicone sealant or mastic to create watertight formwork.

## TYPICAL PROPERTIES

Compressive Strength	95 MPa
Flexural Strength	34 MPa
Tensile Strength	32 MPa
Bond Strength	> 3.5 MPa
Pot Life @ 20°C	30 minutes
Specific Gravity	1.70 gm/ml
Full Cure	7 days

## APPLICATION

Resigrout L is suitable for applications in gaps ranging from 30 – 70mm.

Resigrout L can be poured into formwork for jobs such as grouting base plates, where intimate contact is required between the plate and grouting material. Ensure formwork is watertight by testing with water where possible, and seal edges with Silicone sealant where necessary.

Pour Resigrout L through the formwork in a single continuous application to avoid entrapment of air or water.

## CURING

Formwork can be removed after 24 hours; however, 7 days is required for full cure of this product.

## CLEAN UP

All equipment should be cleaned immediately after use using Resiloc Thinners. Cured material can only be removed mechanically, and with difficulty.

## STORAGE

Resigrout L should be stored in a cool, dry place in original unopened containers. Shelf life under these conditions is 12 months.

## MIXING

Resigrout L is suitable for mixing using a drill and suitable paddle, or by pump where large quantities are required. Mix thoroughly for 3 – 5 minutes to ensure proper mixing. Only mix as much material as can be used within the pot life of the product, and do not attempt to rework or retemper any partially set material.

If not used promptly, liquid epoxy grouts can be subject to exotherm and set prematurely.

## SUPPLY

Resigrout L is available in premeasured 3.5 litre kits or 14 litre kits.

## PRECAUTIONS

Resigrout L is designed for use in ambient temperatures between 10° - 35° C and all properties listed above assume a temperature of 20°C. Where conditions outside this range are encountered, please consult our technical staff prior to application.

Always use all the product within the pot life to avoid waste.

**Material Safety Data Sheets (MSDS) are available to users of Aitken Freeman products on request. Please ensure you have read this data sheet, the MSDS, and the product label carefully before first use of any product.**

## ALLIED PRODUCTS

Aitken Freeman manufactures a broad range of construction products and can supply the following:

- Grouts and anchoring systems
- Epoxy Surface Coatings
- Admixtures for concrete
- Adhesives & Sealants
- Floor toppings
- Floor levelling compounds
- Concrete Repair materials
- Waterproofing solutions

### ***Refer to Material Safety Data Sheet for precautions and personal protection***

**Disclaimer:** Any advice, recommendation, information, assistance or service provided by Aitken Freeman P/L in relation to goods manufactured or supplied by them or their use and application is in good faith and is believed by Aitken Freeman P/L to be appropriate and reliable. However, any advice, recommendation, information, assistance or service provided by Aitken Freeman P/L is provided without liability.

### **Location:**

Factory 7  
7-9 Brough St  
Springvale.Vic.3171  
Ph: 03 9701 3955

[www.aitkenfreeman.com](http://www.aitkenfreeman.com)