


Pavecure A



Water based Acrylic Curing Compound that complies with AS:3799

USES

Pavecure A is suitable for curing all freshly laid concrete either smooth or textured, indoors or outdoors.

BENEFITS

- Dries to a clear finish
- Complies with Australian Standard AS3799
- Achieves water retention of 90% or greater
- Totally water based
- Single pack
- Reduces plastic shrinkage
- Environmentally friendly
- Can be applied by spray, roller or brush
- Will not yellow in sunlight
- Eliminates the need for curing by ponded water, damp hessian or polythene sheeting
- Seals concrete surfaces
- Takes most after trades
- Equipment washable in water

TECHNICAL SUPPORT

Through our experienced sales team, Aitken Freeman can offer technical support to users and specifiers and can arrange on-site visits to end users and contractors.

SUPPLY

Pavecure A is available in either 20 litre or 200 litre drums.

TYPICAL PROPERTIES AND APPLICATION DATA

Appearance:	Milky white emulsion
Coverage:	5m ² per litre
Viscosity:	20 - 22 seconds (Ford #4)
Solids:	40% +/- 1%
Solubility in Water:	Totally soluble
Flash Point:	Not applicable
Solvents:	Not applicable
Shelf Life:	12 months maximum
Dry Time:	Tack Free: 1 - 3 hours Hard Dry: 4 - 8 hours Trafficable: 24 hours
Application Temperature:	10°C - 35°C
Application By:	- Spray - Brush - Roller - Broom
Packaging:	- 205 Lt drum - 20 Lt container
UN Number:	Not applicable
Hazchem Code:	Not applicable
Packaging Group:	Not applicable
Poison Schedule:	Not applicable
Dangerous Goods Class:	Not applicable

INSTALLATION

Apply Pavecure A to the concrete as soon as the bleed water has gone, and the concrete has hardened sufficiently so as not to be marked by the application process.

Apply Pavecure A undiluted at a rate of 1 litre per 5m². Best applied by spray, however, may also be applied by brush, roller or broom.

Note:

Spray equipment should be clean and in good working condition. Otherwise, you will end up in an uneven finish to the surface of the Concrete. Spills and drips will cause blemishes in the surface.

STORAGE

Pavecure A should be stored in a cool, dry place in original unopened containers. Shelf life under these conditions is 12 months.

PRECAUTIONS

Pavecure A is designed for use in ambient temperatures between 5° - 40° C and all properties listed above assume a temperature of 20°C. Where conditions outside this range are encountered, please consult our Technical staff prior to application.

AFTER TRADES

It is recommended that a period of 28 days from the date of pouring has elapsed before any after trades are applied.

Depending on the material to be applied, removal of the Curing Compound may be required, this can be achieved by Grinding or Shotblasting.

CLEANING

Ensure all equipment is thoroughly cleaned with water immediately after use.

Material Safety Data Sheets (MSDS) are available to users of Aitken Freeman products on request. Please ensure you have read this data sheet, the MSDS, and the product label carefully before first use of any product.

ALLIED PRODUCTS

Aitken Freeman manufactures a broad range of construction products and can supply the following:

- Grouts and anchoring systems
- Epoxy Surface Coatings
- Admixtures for concrete
- Adhesives & Sealants
- Floor toppings
- Floor levelling compounds
- Concrete Repair materials
- Waterproofing solutions

Refer to Material Safety Data Sheet for precautions and personal protection

Disclaimer: Any advice, recommendation, information, assistance or service provided by Aitken Freeman P/L in relation to goods manufactured or supplied by them or their use and application is in good faith and is believed by Aitken Freeman P/L to be appropriate and reliable. However, any advice, recommendation, information, assistance or service provided by Aitken Freeman P/L is provided without liability.

Locations:

Vic

Factory 7
7 – 9 Brough St
Springvale.Vic.3171
Ph: 03 9701 3955

WA

6B Chalkley Place
Bayswater.WA.6053
Ph. 1300 816 711

Website

www.aitkenfreeman.com